

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
07.03.2001 Bulletin 2001/10

(51) Int. Cl.⁷: **C08J 7/04, C09D 7/12,**
B65D 81/26

(21) Application number: 00118345.8

(22) Date of filing: 24.08.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 01.09.1999 US 388071

(71) Applicant: **WESTVACO CORPORATION**
New York New York 10171 (US)

(72) Inventors:
• **Faist, Ladislav**
Columbia, MD 21044 (US)

• **Miller, James R.**
Roanoke, VA 24019 (US)
• **Schlek, Mark E.**
Mt. Airy, MD 21771 (US)
• **Walker, David R.**
Charleston, SC 29407 (US)

(74) Representative:
Stoffregen, Hans-Herbert, Dr. Dipl.-Phys.
Patentanwalt,
Friedrich-Ebert-Anlage 11b
63450 Hanau (DE)

(54) **Method for making odor sorbing packaging material**

(57) An odor sorbing packaging material is prepared by applying to at least one surface of a flexible substrate an odor absorbing coating containing an effective concentration of activated carbon. The packaging material may be converted into packages, bags, pouches, liner members, wrappers or the like for packaging products and other materials that generate objectionable odors.

Description**Background of the invention**

5 [0001] The present invention relates generally to a novel odor sorbing packaging material and more particularly to a method for preparing such a material that can be converted into packages for products which generate objectionable odors.

[0002] One of the most widely accepted materials used to absorb odors is activated carbon. Activated carbon is used in paperboard packaging, filters, gas masks and other devices to absorb and trap objectionable odors, aromas and other impurities. For example United States Patents Nos. 5,540,916 and 5,693,385, owned by the present assignee
 10 herein, disclose an odor sorbing packaging material comprising paperboard onto which there is applied a coating comprising activated carbon. Other prior art which discloses paper-based packaging containing activated carbon includes United States Patent Nos. 2,593,146 which discloses laminated sheets for wrapping foodstuffs, and United States Patent No. 3,149,023 which discloses treated paperboard for packaging. United States Patent No. 4,504,290 discloses a
 15 filter element which contains activated carbon for odor control; United States Patent No. 4,517,308 discloses the use of activated carbon in filter mats, air fresheners, inner soles for shoes etc.; United States Patent No. 5,022,553 discloses a diaper storage container having a substantially rigid inner liner containing activated carbon; and, United States Patent No. 5,860,391 discloses the use of activated carbon in animal litter. However, as will be noted, in each of the prior art teachings, the activated carbon applications have been made primarily to rigid or semi-rigid products. Accordingly, it is
 20 an object of the present invention to incorporate activated carbon into a non-rigid structure in an expeditious, economical and effective manner.

Summary of invention

25 [0003] The present invention relates generally to packaging materials and more specifically to a substantially flexible packaging material that has been treated to absorb the odors and aromas given off by products contained within packages constructed from the packaging material. For this purpose, the present invention employs activated carbon, a material well known for its ability to absorb objectionable odors. In a preferred embodiment, the activated carbon is applied to one or both surfaces of a flexible, polymeric film material using conventional technology. However it is contemplated that other flexible substrates such as paper onto which there is applied a polymer coating, or laminates of
 30 paper and polymer films could be used.

[0004] Activated carbon materials such as the NUCCHAR products sold by Westvaco Corporation (the assignee herein), are available in particle sizes, or can be ground to particle sizes, which are readily dispersable in coatings, inks or the like suitable for application to flexible film materials such as polyolefins. After application of the activated carbon
 35 to the film materials, the treated film can be converted into packages, liner elements, trash bags, pouches, wrappers or the like suitable for use in many different applications where odor absorption is desired.

[0005] It is therefore, an object of the present invention to provide an improved method for applying an odor sorbing coating to packaging material.

[0006] It is another object of the invention to provide an odor sorbing packaging material with a sufficient concentration of activated carbon to accomplish the purpose of deodorizing substantially the entirety of packages converted from the packaging material.
 40

[0007] And, finally, it is an object of the invention to provide an substantially flexible odor sorbing packaging material that may be converted into various packages useful for a variety of purposes which require odor control.

[0008] To satisfy these and other objects of the present invention contemplates the use of activated carbon dispersed in a binder that can be applied to a polymeric film. Sub-micron carbon black is known for use as a coloring pigment in the manufacture of polyethylene resins to produce black trash bags. However, attempts to use typical odor
 45 sorbing activated carbons of larger particle size (5-40 microns) have been unsuccessful because the presence of the particles have produced films with holes (voids) at higher carbon concentrations, or low odor sorbing capacity at low carbon concentration. Likewise, attempts to apply an aqueous coating containing activated carbon to a polyolefin film have been less than successful. Such attempts have produced, on the one hand, coatings with a low carbon content
 50 (less than about 60%), that adhered well, but performed poorly in odor tests, or coatings with a carbon content greater than about 80%, with good odor sorption characteristics, but poor adhesion and excessive carbon rub-off. To overcome these problems, the present invention was developed. The present invention solves the problems referred to hereinbefore by applying the activated carbon containing coating in two steps.

Detailed Description

[0009] The present invention is directed to the use of activated carbon in the manufacture of an odor absorbing

EP 1 081 181 A1

packaging material. In the preferred embodiment, the packaging material comprises a substantially flexible polymer substrate onto which there is applied a coating containing activated carbon.

[0010] In one form of the present invention the substrate comprises a low density polyethylene (LDPE) film upon which activated carbon in an aqueous coating composition containing a suitable binder that adheres well to LDPE is applied by conventional techniques such as coating, printing or the like. While LDPE is disclosed herein as a preferred substrate, other polymer films could readily be substituted with a suitable binder material. Examples of such polymer films are polypropylene, polyester, and polyamide.

[0011] An example of a suitable binder material for the preferred LDPE substrate is an aqueous styrene acrylate emulsion (identified as JONREZ E-2064 from Westvaco Corporation's Chemical Division), that wets out the LDPE film to provide acceptable adhesion. "Wets out" in this context means that the emulsion spreads easily on the film surface without beading up. An aqueous binder system is preferred for the present invention as opposed to a solvent based system for environmental reasons and because solvent recovery systems are complex and costly.

[0012] Initial coatings with up to 50% by weight of activated carbon having a particle size of about 5 microns adhered easily to LDPE film without appreciable rub off, but performed poorly in odor absorption tests. With 60% or more by weight activated carbon applied, significant rub off occurred and the products were deemed unacceptable. In order to increase the concentration of carbon on the surface and reduce rub off, a two step process for applying the coatings was adopted.

[0013] The two step procedure involves an initial application of a primer coating that may contain from about 0-50% by weight activated carbon, followed by a second coating application comprising a carbon/binder mixture of up to about 95% by weight activated carbon and the remainder binder. The second application comprising up to 95% carbon adheres well to the first primer layer with no appreciable rub off and achieves a high concentration of activated carbon on the film surface to achieve good odor control.

[0014] Odor panel testing of samples prepared according to the invention demonstrated the effectiveness of the two step process. The results of the tests are shown in Table I.

Table I

Odor Panel Testing		
Carbon Sample	1 hour	24 hours
Odor (onion)	5	5
100% Binder	3.5	3.5
Carbon Powder	3.5	2
50% Carbon/50% Binder	2	1
1st Step: 100% Binder	1	1
2nd Step: 95% Carbon/5% Binder		
Odor Rating: (no odor) 1.....5 (strong odor) One drop of onion juice per jar. LDPE substrate.		

[0015] The test samples contained equivalent amounts of activated carbon. For example, almost twice the surface area of the 50/50 carbon/binder coating was used compared with the 95/5 sample prepared with two steps. The results indicate that the 50/50 coating was substantially as effective at negating the onion odor after 24 hours as the 95/5 sample, however the latter coating with a greater concentration of activated carbon at the film surface was more effective after 1 hour.

[0016] Accordingly it will be seen that the novelty of the present invention lies in the technique for applying the greatest concentration of carbon available at the film surface with little or no rub off. The amount of carbon necessary to accomplish the desired odor abatement result will depend in the first instance upon the strength of the odor desired to be eliminated or absorbed. For the purposes of the present invention, an effective application of activated carbon is intended to mean sufficient carbon to absorb substantially all of the odor present in the packaged product or waste. Since the total amount of carbon required for any specific application cannot be defined with any specificity, a trial and error process may be involved.

[0017] While only a preferred embodiment of the present invention has been fully described, it will be obvious to those skilled in the art that various modifications and substitutions could be made in the invention without departing

from the scope of the invention as defined in the appended claims.

Claims

- 5 1. A method for making a substantially flexible odor absorbing packaging material comprising:
 - (a) selecting a flexible substrate;
 - (b) preparing a first odor sorbing coating composition consisting essentially of activated carbon and binder wherein said binder is capable of wetting out the surface of the substrate of step (a);
 - 10 (c) applying the first odor sorbing coating to the substrate of step (a);
 - (d) drying the coating of step (c);
 - (e) preparing a second odor sorbing coating composition consisting essentially of activated carbon and binder wherein the concentration of activated carbon in the second coating is greater than the activated carbon concentration of the first coating;
 - 15 (f) applying the second odor sorbing coating to the substrate over the dried residue of the first coating; and,
 - (g) drying the substrate.
2. The method of claim 1 wherein the flexible substrate is a polymeric film selected from the group consisting of polyolefins, polyesters, and polyamides.
- 20 3. The method of claim 2 wherein the binder component of the two coating compositions of steps (b) and (e) comprises an aqueous emulsion selected from the group consisting of styrenes, acetates, and urethanes.
4. The method of claim 3 wherein the carbon content in the first coating composition comprises 0-50% by weight activated carbon.
- 25 5. The method of claim 4 wherein the carbon content in the second coating composition comprises 50-95% by weight activated carbon.
- 30 6. The method of claim 5 wherein the activated carbon has a particle size within the range 5-40 microns.
7. The method of claim 6 wherein the flexible substrate is low density polyethylene.
8. The method of claim 7 wherein the binder is an aqueous emulsion of styrene acrylate.
- 35 9. Odor absorbing packaging material comprising a substantially flexible substrate having applied to at least one surface thereof an odor sorbing coating wherein said coating comprises from about 50-95% by weight activated carbon and from about 5-50% by weight binder.
- 40 10. The packaging material of claim 9 wherein said substrate comprises a polymeric film selected from the group consisting of polyolefins, polyesters and polyamides.
11. The packaging material of claim 10 wherein said binder comprises an aqueous emulsion selected from the group consisting of styrenes, acetates, and urethanes.
- 45 12. The packaging material of claim 11 wherein the substrate is low density polyethylene and the binder is an aqueous emulsion of styrene acrylate.
- 50 13. A substantially flexible odor absorbing packaging material made by the method of claim 1.

EP 1 081 181 A1



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 11 8345

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (InCL17)
A	<p>DATABASE WPI Week 8410 Derwent Publications Ltd., London, GB; AN 1984-059495 XP002154180 & JP 59 017353 A (NEOFILTER KOGYO KK), 28 January 1984 (1984-01-28) * abstract *</p>	1	<p>C08J7/04 C09D7/12 B65D81/26</p>
A	<p>DATABASE WPI Week 9316 Derwent Publications Ltd., London, GB; AN 1993-131036 XP002154181 & JP 05 069516 A (KAWASHIMA ORIMONO KK), 23 March 1993 (1993-03-23) * abstract *</p>	1	
D,A	<p>US 5 693 385 A (PARKS CHRISTOPHER J) 2 December 1997 (1997-12-02) * claim 9 *</p>	1	
A	<p>EP 0 587 293 A (COURTAULDS TEXTILES HOLDINGS) 16 March 1994 (1994-03-16) * claims 1,2 * * column 2, line 1 - line 8 * * column 3, line 32 - line 41 *</p>	1,2	<p>TECHNICAL FIELDS SEARCHED (InCL17)</p> <p>C08J C09D B65D</p>
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 30 November 2000	Examiner Hallemesch, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1803 (03.02.99) (P.02/01)

EP 1 081 181 A1

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 8345

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

30-11-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 59017353 A	28-01-1984	NONE	
JP 5069516 A	23-03-1993	NONE	
US 5693385 A	02-12-1997	US 5540916 A	30-07-1996
EP 0587293 A	16-03-1994	DE 69301984 D	02-05-1996
		DE 69301984 T	31-10-1996
		ES 2088808 T	16-09-1996
		JP 6212145 A	02-08-1994

EPO FORM P0499

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82